Temperature (C)	Absolute Viscosity (mPa-s)	Source
183.4	0.5918	4
190.8	0.8944	1
193.2	0.5749	4
194.8	0.8099	1
195.6	0.7744	1
195.8	0.7684	1
196.4	0.7504	1
200	0.569	3
206.4	0.6102	1
206.6	0.624	1
207.1	0.6054	1
207.2	0.6492	1
207.8	0.6206	1
208.1	0.5541	4
216	0.5406	4
229.5	0.7019	1
229.5	0.6758	1
229.5	0.6561	1
229.7	0.6905	1
229.7	0.6602	1
250.8	0.4917	4
254.6	0.6352	1
255	0.6536	1
255.2	0.6494	1
255.2	0.6136	1
255.5	0.5951	1
285.5	0.4548	4
289.8	0.5754	1
289.9	0.5609	1
290.1	0.61	1
290.3	0.6345	1
314.1	0.5335	1
314.2	0.5451	1
314.2	0.5437	1
314.6	0.5255	1
314.7	0.5232	1
378.1	0.5125	1
378.7	0.4258	1
379.2	0.4383	1
379.3	0.4237	1
380.1	0.4222	1
400	0.374	3
422.9	0.4175	1
423.1	0.4394	1
423.3	0.4106	1
423.5	0.4275	1
425.4	0.4579	1
477.2	0.398	1

477.5	0.3993	1
477.6	0.3961	1
477.7	0.4141	1
478.1	0.4239	1
536.7	0.3662	1
536.8	0.3515	1
537.4	0.347	1
539.8	0.383	1
540.1	0.4307	1
540.2	0.3661	1
600	0.312	2
600	0.283	3
643.2	0.3441	1
643.4	0.3611	1
643.9	0.3616	1
644	0.3208	1
644.2	0.3716	1
757.6	0.3479	1
758.6	0.3476	1
758.7	0.352	1
758.7	0.3472	1
759	0.3398	1
800	0.218	2
800	0.231	3
872.4	0.2288	1
873.1	0.265	1
873.4	0.2801	1
875.7	0.2301	1
878.3	0.2325	1
1000	0.171	2
1000	0.196	3
1200	0.143	2

Sources

1. P. Y. Achener and D. L. Fisher,
   "Alkali Metals Evaluation Program - Viscosity of Liquid Sodium and Lithium,"
   AGN-8191, Vol. 5, Aerojet General Corporation, May 1967.

2. D. V. Rigney et al.,
   "The Viscosity of Lithium,"
   Pratt and Whitney Aircraft (CANEL), Report TIM-849, 1965.

3. E. E. Shpil'rain et al.,
   "Experimental Investigation of Thermal and Electrical Properties
   of Liquid Alkali Metals at High Temperatures,"
   High Temperature, 3(6), pp. 870-874 (1965),
   translated from Teplofiz.Vysakikh Temperatur,
   Akad.Nauk SSR, 3(6), pp. 930-933 (1965).

4. E. N. da C. Andrade and E. R. Dobbs,
   "The Viscosities of Liquid Lithium, Rubidium, and Caesium,"
   Proceedings Royal Society A, Vol. 211, pp. 12-30 (1952).